

Liquid Paraffin

Item	Parameters	ASLC103	ASLC148	ASLC203	ASLC248	ASLC303	ASLC348	ASLI116	ASLI2612	Test Method
1	Flash Point °C	Min 180	Min 180	Min 180	Min 180	Min 180	Min 180	Min 180	Min 180	ASTM D-92
2	Kinematic Viscosity 40 °C	16-24	16-24	16-24	16-24	16-24	16-24	16-24	16-24	ASTM D-445
3	Pour Point °C	-12 TO -6	-12 TO -6	-6 TO 0	-6 TO 0	0 TO +5	0 TO +5	-12TO-3	-3 TO +6	ASTM D-97
4	Color (Lovi Bond)	0.0 - 0.3	0.4 - 0.8	0.0 - 0.3	0.4 - 0.8	0.0 - 0.3	0.4 - 0.8	0.1 - 0.6	0.6 - 1.2	IP- 17Cell1"
5	Sp -Gravity @ 25 °C	0.760 - 0.850	0.760 - 0.850	0.760 - 0.850	0.760 - 0.850	0.760 - 0.850	0.760 - 0.850	0.760 - 0.850	0.760 - 0.850	ASTM D-1298
6	Polycyclic Aromatic Hydrocarbon	Passed	Passed	Passed	Passed	Passed	Passed	---	---	BP-2012
7	Heavy Metals (Pb &AS)	Passed	Passed	Passed	Passed	Passed	Passed	---	----	ISIRI-5812
8	Solid Paraffin	Passed	Passed	Passed	Passed	Passed	Passed	Passed	Passed	ISIRI-5812