

Liquid Paraffin

| Item | Parameters | ASLC203 | ASLC303 | ASLI2612 | ASLI3612 | ASLP201 | Test Method |
|------|---------------------------------|---------------|---------------|---------------|---------------|---------------|-------------|
| | Ranking | 1 | 2 | 1 | 2 | 1 | |
| 1 | Flash Point °C | Min 180 | Min 180 | Min 180 | Min 180 | Min 180 | ASTM D92 |
| 2 | Kinematic Viscosity 40 °C | 16-24 | 16-24 | 16-24 | 16-24 | 16-24 | ASTM D445 |
| 3 | Pour Point °C | -9 TO -3 | 0 TO +6 | -9 TO -3 | 0 TO +6 | -9 TO -3 | ASTM D97 |
| 4 | Color (LoviBond) | 0.0 - 0.3 | 0.0 - 0.3 | 0.6 - 1.2 | 0.6 - 1.2 | 0.0 - 0.1 | IP17 Cell1" |
| 5 | Color (Saybolt) | +30 | +30 | Max +25 | Max +25 | +30 | ASTM D156 |
| 6 | Sp -Gravity @ 25 °C | 0.760 - 0.850 | 0.760 - 0.850 | 0.760 - 0.850 | 0.760 - 0.850 | 0.760 - 0.850 | ASTM D1298 |
| 7 | Polycyclic Aromatic Hydrocarbon | Pass | Pass | --- | --- | Pass | BP 2020 |
| 8 | Heavy Metals (Pb & AS) | Pass | Pass | ---- | ---- | Pass | ISIRI 5812 |
| 9 | Solid Paraffin | Pass | Pass | Pass | Pass | Pass | ISIRI 5812 |